Experimental Investigation on Strength Behaviour between GFRP & Steel Bars Reinforced in Columns

M. Priyashagadevan

PG Student Department of Civil Engineering Valliammai Engineering College, Chennai

K. A. Kalaiarasi

Assistant Professor Department of Civil Engineering Valliammai Engineering College, Chennai

Abstract

Glass Fiber Reinforced Polymer (GFRP) is a composite material, which consist of polyester thermosetting resin as matrix and glass fibers as reinforcement. Pultrusion technique is used to fabricate GFRP products in various continuous forms of structural sections such as box, I-, H-, and plates, which are similar as steel sections. The use of GFRP member in structures is relatively becoming more important especially in constructions. It was observed that the current required technical and design data of pultruded GFRP sections was rather limited especially about material properties and structural performance. This study was conducted experimentally to investigate the physical and mechanical properties of the GFRP.

Keywords- Non-Corrosive Material, Compression Strength, Split Tensile Strength of GFRP Bars

I. INTRODUCTION

Fiberglass refers to a group of products made from individual glass fibers combined into a variety of forms. Glass fibers can be divided into two major groups according to their geometry continuous fibers used in yarns and textiles, and the discontinuous (short) fibers used as batts, blankets, or boards for insulation and filtration. Fiberglass can be formed into yarn much like wool or cotton, and woven into fabric which is sometimes used for draperies. Fiberglass textiles are commonly used as a reinforcement material for molded and laminated plastics. Fiberglass wool, a thick, fluffy material made from discontinuous fibers, is used for thermal insulation and sound absorption. It is commonly found in ship and submarine bulkheads and hulls; automobile engine compartments and body panel liners; in furnaces and air conditioning units; acoustical wall and ceiling panels; and architectural partitions. Fiberglass can be tailored for specific applications such as Type E (electrical), used as electrical insulation tape, textiles and reinforcement; Type C (chemical), which has superior acid resistance, and Type T, for thermal insulation. The basic raw materials for fiberglass products are a variety of natural minerals and manufactured chemicals. The major ingredients are silica sand, limestone, and soda ash. Other ingredients may include calcined alumina, borax, feldspar, nepheline syenite, magnesite, and kaolin clay, among others. Silica sand is used as the glass former, and soda ash and limestone help primarily to lower the melting temperature. Other ingredients are used to improve certain properties, such as borax for chemical resistance. Waste glass, also called cullet, is also used as a raw material. The raw materials must be carefully weighed in exact quantities and thoroughly mixed together (called batching) before being melted into glass.

II. EXPERIMENTAL PROGRAMME

In this experimental program involves various processes of material testing, mix proportioning, mixing, casting and curing of test specimens. All the testing on materials was done in material testing laboratory, Valliammai engineering college Chennai.

A. Materials Used

The materials used in the preparation of concrete mix include cement, fine aggregates, coarse aggregates, GFRP rebar and steel bars. All the materials were tested and its physical properties are described below.

1) Cement

Ordinary Portland cement of 43 grade was used, conforming to recommendations stated in IS 403(1999). The normal consistency and initial setting time of cement was 30% and 30 minutes respectively.

2) Fine Aggregate

Coarse sand locally available is taken as fine aggregate. The test procedures as mentioned in IS-383(1970) were followed to determine the physical properties of fine aggregate as shown in Table 1.

3) Coarse Aggregate

The aggregates were tested in accordance to IS-383(1970). The results obtained are tabulated in Table 2.

4) Glass Fiber Reinforced Polymer

The basic raw materials for fibre glass products are a variety of natural minerals and manufactured chemicals. The major ingredients are silica sand, limestone, and soda ash. Other ingredients may include calcined alumina, borax, feldspar, nepheline syenite, magnesite, and kaolin clay, among others. Silica sand is used as the glass former, and soda ash and limestone help primarily to lower the melting temperature. Other ingredients are used to improve certain properties, such as borax for chemical resistance. Waste glass, also called cullet, is also used as a raw material. The raw materials must be carefully weighed in exact quantities and thoroughly mixed together (called batching) before being melted into glass.

5) Water

As per recommendation of IS: 456(2000), the water to be used for mixing and curing of concrete should be free from deleterious materials. Therefore, potable water was used in the present study in all operations demanding control over water quality.



Fig. 1: GFRP Bars

Table 1. Enysical Froperties of Fine Aggregate				
Physical properties	Observed Values	Recommended Values		
Grading Zone	2	-		
Fineness Modulus	2.70	2.9-3.2		
Specific Gravity	2.54	2.3-2.67		

Table 1: Physical Properties of Fine Aggregate

Table 2: Physical Properties of Coarse Aggregate			
Physical properties	Observed Values	Recommended Values	
Fineness Modulus	2.58	2.3-2.67	
Specific Gravity	6.87	6.5-8.0	
Aggregate crushing value (%)	34.5	Not more than 45%	
Aggregate impact value (%)	32.5	Not more than 45%	
Table 3: Physical Properties of GFRP Bar			

Physical properties	Recommended values from testing		
Diameter of bar	12mm		
Young's modules	298970		
Tensile strength (N/mm2)	586.6 N/mm2		
Table 4: Physica	al Properties of Steel Bar		
Physical properties	Recommended values from testing		
Diameter of bar	12mm		

Young's modules	200000	
Tensile strength (N/mm2)	486N/mm2	

B. Methodology

As per IS 10262: 2009 the mix proportion of concrete was done. To achieve specified characteristics at specific age, workability of fresh concrete and durability requirements proportioning is carried out. Grade M30 was proportioned according to the procedure as mentioned in the code.

C. Mixing of Concrete, Casting and Curing of Test Specimens

The machine mixing was done during the entire process of casting. First the dry mix contains cement; coarse aggregate and fine aggregate was mixed for 2 minutes and with the addition of water again it will mix for 2 minutes until the mixture attains the homogeneous. Compaction was achieved by means of damping rod manually. All the specimens were demolded after 24 hours and stored in curing tank until the age of testing.

D. Test Methods

The fresh concrete was tested for slump. Then the hardened concrete was tested for compressive strength and discussed below.

1) Workability Test

As per IS 1199-1959 slump test was done to find the workability. Slump cone test is the quick measure of workability of concrete mixes.

2) Compressive Strength Test

As per IS 516: 1959 compressive test was performed the test program consists of casting and testing three Columns in given size 150 x 150 x 900mm. The test specimen is mounted in a column testing frame of 500 kN capacity. The Column are 900mm in length and it is pinned supported. The load is applied at gradually which starts from the load 200 KN.

3) Tensile Test

Tensile properties of bar and steel are tested and calculated by tensile machine.

STEEL

12mm



Fig. 2: Tensile test on GFRP Bar

Table 4: Tensile Strength on GFRP & Steel Bar					
TYPE	DIAMETER OF BAR	AREA(MM ²⁾	TENSILE STRENGTH (N/mm ²)	PEAK LOAD (KN)	YOUNGS MODULUS
GERP	12mm	113	586 675	66 3/0	208070

113

Fable 4: Tensile Strength on GFRP & Steel Ba

III. RESULTS AND DISCUSSION

486

55.41

The testing is carried out for 2 types of columns. Various comparisons were made in this test with these columns and the major parameters compared are strength, deflection, and various crack patterns of the columns.

200000



Fig. 3: Compression Test on GFRP & Steel Column

The columns are tested by using compression testing machine. The loads are applied at gradually increasing up to the point of the cracks are obtained at initial stage. After that each load point is noted carefully until the ultimate load is occurred. The deflection of the columns are noted for the both GFRP and steel reinforced columns. By the test result we are able to know that GFRP column has more load carrying capacity than the steel reinforced column. Its nearly 10% to 20% of additional load carrying capacity of the GFRP column than the steel reinforced column.

So it's proved that GFRP reinforced structures are able carry more loads than the steel reinforced structures. The durability of the structure is also more occurs by the GFRP structure.

We can see the comparison table and load deflection curve for the GFRP and steel reinforced Colum

A. Various Strength Criteria of Specimens

Representative crack patterns after the test for the Column and specimens in the various test series are given. The cracking patterns for the specimens were quite similar when subjected to externally applied load. All specimens (control and strengthened) developed their first cracks within the constant region during initial loading. As the applied load increased, the cracks increased in number and started to develop as the load increased to failure, the cracks tended to fork out, and additional cracks formed.

S.no	Specimen Details	Ultimate load (ken)	
1	Reinforcement COLUMN	297	418.5
2	GFRP COLUMN	378	475.7

The testing is carried out for 2 types of columns. Various comparisons were made in this test with these columns and the major parameters compared are strength, deflection, and various crack patterns of the columns.



DISPLACEMENT (MM) Fig. 4: Load Deflection Curve for GFRP Reinforced Column



Fig. 5: Load Deflection Curve for Steel Column Reinforcement

In recent years, the using of GFRP has been successful for different concrete structure members. Although, the behavior of RC short columns has not been yet fully explored. The present study aims to provide basic technical information about the behavior of concrete column, reinforced longitudinally and transversally with GFRP bars and stirrups through experimental investigation and analytical study.

IV. CONCLUSIONS

Based on the experimental results carried out in this research considering the previous parameters associated with this research program, the following general conclusions can be drawn:

- 1) The GFRP and steel RC columns behaved in an analogous manner and exhibited linear load-strain behavior in the ascending part up to 15% of their peak loads.
- 2) The axial capacities of the GFRP RC columns were on average 10% to 20% higher than their steel RC counterparts.
- 3) The tensile strength of GFRP bar is also more than steel bar.
- 4) Since GFRP reinforcement is more effective at highly corrosion areas, it is more attractive and recommended to be used in field applications.

ACKNOWLEDGEMENT

The inception and the rudimentary concepts of project are ascribable to my guide Ms.K.A.KALAIARASI, M.E., Assistant Professor, Department of Civil Engineering, without whose invaluable guidance, patient and encouragement, anything would have materialized. I owe my gratitude to her.

REFERENCES

- [1] Afifi, M. Z., Mohamed, H., and Benmokrane, B., [2013a]. Axial Capacity of Circular Concrete Columns Reinforced with GFRP Bars and Spirals. | Journal of Composites for Construction, in press.
- [2] American Concrete Institute (ACI) Committee 440, [2006]. Guide for the Design and Construction of Concrete Reinforced with FRP Bars, ACI 440.1R-06, Farmington Hills, Mich.
- [3] Issa, M. S., Metwally, I. M., and Elzeiny, S. M. [2011]. —Structural Performance of Eccentrically Loaded GFRP Reinforced Concrete Columns. International Journal of Civil and Structural Engineering, 2(1), 395–404.
- [4] Lotfy, E. M. [2010]. —Behavior of Reinforced Concrete Short Columns with Fiber Reinforced Polymers Bars." International Journal of Civil and Structural Engineering, 1 (3), 545-557.
- [5] Mirmiran, A. and Shahawy, M., [1997]. "Behavior of Concrete Columns Confined by Fiber Composites." Journal of Structural Engineering, 123 (5), 583-590.
- [6] Zadeh, J. H., and Nanni, A. [2013]. Design of RC Columns using Glass FRP Reinforcement. Journal of Composite for Construction, 17(3), 294-304.